Chemistry – Food Chemistry


Biochemistry - Microbiology

Material Testing - Expert Opinions

Chemical Laboratory Dr. Stegemann Leimbrink 2 – D-49124 Georgsmarienhütte

HAHN Kunststoffe GmbH

Gebäude 1027 D-55483 Hahn-Flughafen



From the chamber of commerce publicy appointed and sworn court-appointed expert for chemistry, chemistry of waste, physical and chemical tests of synthetic materials, oils, building materials and corrosion

Authorized chamber of Commerce Osnabrück-Emsland-County Bentheim

Water-Waste Water-Drinking Water -Technical Water-Groundwater-Soil-Food-Hygiene-Objects of Daily Use-Industrial Waste-Advisory Service in Waste Water Disposal-Material Testing-Court Experts Evidence for Material Damages-**Expert Opinions on Emission Control**

26.07.2021

EU Declaration of Compliance

1912 121070028

page 1 of 2

Hereby we confirm that the plastic:

HAHN 9006889

complies with the following act:

Commission Regulation (EU) No 10/2011 of 14 January 2011 (last update 08/2016) on plastic materials and articles intended to come into contact with food as a specific regulation referring to the regulation No 1935/2004 of the European Parliament.

The overall migration according to annex 1 of the regulation lies among the regulatory limit of the Commission Regulation (EU) No 10/2011 for the applied contact times, contact temperatures and contact simulants subsequently mentioned.

Specification of the intended contact

intended use : different applications

intended food contact for which the

compliance can be confirmed

: all kind of food1

related simulants according to : Ethanol 10 % (simulant A)

Acetic Acid 3 % (simulant B) Annex III part 4

> Ethanol 95 % (simulant D2 replacement) Isooctane (simulant D2 replacement)

related test conditions (overall migration) : 20 min at 50 °C 2

for which the compliance can be

confirmed

: 07.07.2021 - 13.07.2021 test period

Accredited Laboratory:

Communication:

Tel. 0049 5401 8636-0 FAX 0049 5401 8636-36 e-mail: info@labor-stegemann.de www.labor-stegemann.de





¹according to Annex III Table 3 regulation EU 10/2011

²modified according to the worst case possible contact time and contact temperature

Continuation of the Declaration of Compliance No. 1912-121070028 from 26.07.2021

Test results¹

Simulant	Overall Migration mg/dm ² DIN EN 14338 / DIN EN 1186	Limit Value mg/dm²
Ethanol 10 % simulant A	3,2	10,0
Acetic Acid 3 % (simulant B)	2,6	10,0
Ethanol 95 % (simulant D2 replacement)	4,2	10,0
Isooctane (simulant D2 replacement)	8,6	10,0

D. Ategomoum

Dr. Dirk Stegemann - Test Chord -

Dr. Dirk Stegemann
Bestellungsgebiet:
Chemic, insbesondere Chemie
oer Abfallstoffe;
chemisch-physikalische
Untersuchunger von
Kurststoffen, Ölen,
Baustoffen,
Korresioren

From the Lower Saxony State Office for Consumer Protection Food Safety officially approved cross check expert for microbiological and chemical analysis and assessment of food and commodities of all kind

Page 2 of 2

¹ The cartridge was tested as a whole with all components